

PRODUCT DATASHEET

SF 3500

Flexitallic SF 3500 is a superior performance aramid/inorganic fibre sheet sealing material bound with a high quality nitrile rubber. SF 3500 complies with the requirements of the BS 7531 Grade X Specification.



Service:

Specifically designed for sealing split-case pumps handling high pressure water, SF 3500 is also suitable for general industrial applications where an asbestos-free sheet is desirable.

Maximum recommended temperature:
440°C (825°F)

Maximum recommended pressure:
14 MPa (140 bar; 2030 psi)

Note:

These temperature and pressure guides cannot necessarily be used simultaneously and may not apply at all thicknesses.

Do NOT use gasket pastes.

Availability:

For its intended service use SF 3500 is produced 0.4 mm thick. Higher thicknesses may be available on request.

Also available with SARK III release coating on both sides.

Colour: Red

Typical Physical Properties:

Thickness	0.4mm
Density	1.60gcm ⁻³
ASTM Compressibility	11%
ASTM Recovery	62%
ASTM Tensile Strength	20 MPa
DIN Gas Permeability	0.01mL/min
ASTM Oil 3 Thickness Increase	4%
ASTM Fuel B Thickness Increase	8%

This Data Sheet refers to the material as supplied. The information contained herein is given in good faith, but no liability will be accepted by the Company in relation to same.

We reserve the right to change the details given on this Data Sheet as additional information is acquired. Customers requiring the latest version of this Data Sheet should contact our Applications Engineering Department.

The information given and, in particular, any parameters, should be used for guidance purposes only. The Company does not give any warranty that the product will be suitable for the use intended by the customer.

PRODUCT DATASHEET

Health & Safety:

Because of the binding processes which take place during manufacture, the product is believed to present no health and safety hazard and, under normal handling and use it is unlikely that the product will give rise to significant levels of exposure to constituent materials.

Flexitallic SF 3500 is reinforced with glass and aramid fibres. Small amounts of crystalline silica may also be present in the filler material.

Under harsh mechanical treatment (e.g. high speed stamping operations or abrasion) or if the product has become embrittled by high temperature applications, the constituents may give rise to irritant dust which, in extreme cases of exposure, could lead to more serious respiratory problems.

Occupational exposure to such dusts should therefore be minimised and kept below relevant national exposure limits. Flexitallic has adopted an in-house fibre Control Limit of 0.5 fibre per millilitre of air (8 hour TWA) for asbestos-free fibres which may be respirable.

Good standards of hygiene should be applied during gasket cutting operations and off-cuts should be disposed of by transfer to a site appropriately licensed to accept industrial materials of this nature.

Although the reinforcing fibres and fillers are inherently flame resistant, at elevated temperatures or in a sustained fire, decomposition will occur and give rise to irritant and in some instances harmful or toxic fumes.

For further Health and Safety information please see the relevant Material Safety Datasheet or contact Flexitallic UK Ltd.